

KIMBERLY-CLARK* Nitrile Gloves

Chemical Resistance Guide



Chemical Resistance Guide



Incidental Exposure Only

KIMBERLY-CLARK® Nitrile gloves are thin gauge disposable gloves designed to provide barrier protection and tactile sensitivity to the wearer. Our thin mil gloves are not designed for applications involving prolonged, direct exposure to chemicals. Our intent in providing this chemical compatibility information is to provide a guideline for use of our thin mil gloves in applications where incidental splash exposure to various chemicals may occur. Gloves should be removed and replaced immediately if incidental splash exposure occurs.

How to Use this Guide

Two categories of data are used to determine a color code for each chemical:

1. Permeation Breakthrough Time
2. Chemical Boiling Point

Criteria for Chemical Resistance Rating

Permeation Breakthrough Time (PB)

Rating	Minutes
Excellent (E)	60-480
Good (G)	10-59
Poor (P)	1-9
Not Recommended (NR)	< 1

Boiling Point

Volatility	Temp.
High Volatility	<24° C
Low Volatility	>24° C

Precaution: This data was generated from the KIMBERLY-CLARK® STERLING® Nitrile Exam Gloves. This data does not represent gloves thinner than the STERLING® Nitrile glove, such as the KLEEN-GUARD® G10 Arctic Blue Nitrile Gloves.

Color Code Rating System

A glove/chemical combination receives a **GREEN** rating if:

- The permeation breakthrough time is excellent or good and the chemical has high volatility.
- OR**
- The permeation breakthrough time is excellent and the chemical has low volatility.

A glove/chemical combination receives a **YELLOW** rating if:

- Any glove/chemical combination does not meet either set of conditions required for a **GREEN** or **RED** rating.

A glove/chemical combination receives a **RED** rating if:

- The permeation breakthrough time is poor and the chemical has low volatility.
- OR**
- The permeation breakthrough time is not recommended and the chemical has either high or low volatility.

Interpreting Chemical Resistance Ratings

GREEN

The results for this specific chemical suggest that the glove would provide an adequate barrier for use in most applications.

YELLOW

The results require additional consideration to determine suitability for use.

RED

Not recommended for use.

For additional information on choosing the right chemical glove for your application, please visit our Chemical Resistance Database at: <http://www.kcprofessional.com/us/mkt/ChemicalSelectorGuide/>

Chemical Name	Permeation Time (minutes) ASTM F739	Permeation Rate (pg/cm ² /min) ASTM F739	Concentration	Color Code Rating
Acetaldehyde	<1	353	99.5%	
Acetic Acid	5	482	99.7%	
Acetone	1	466	99.5%	
Acetonitrile	1	329	99%	
Acrylic Acid	1	57.8	99%	
Ammonium Hydroxide	7	395	30%	
Amyl Acetate	4	261	99%	
Analine	7	74.7	99.5%	
Benzaldehyde	78	0.57	99.5%	
Benzene	<1	627	99.8%	
Benzyl Alcohol	5	86.8	99%	
n-Butanol	10	5.99	99.8%	
Butyl Acetate	3	233	99%	
Carbon Disulfide	2	3.81	99%	
Carbon Tetrachloride	5	48.9	99.5%	
Chloroform	1	958	99%	
Citric Acid	>480	Not Detected	50%	
Cyclohexane	>480	Not Detected	99.7%	
Cyclohexanol	112	1.18	99%	
Cyclohexanone	1	787	99.8%	
d-Limonene	107	0.157	97%	
n-Dibutyl Phthalate	>480	Not Detected	99%	
1,2-Dichlorobenzene	<1	1179	99%	
Dichloromethane	1	2006	99.9%	
Diesel Fuel, mixture	160	0.63	Mixture	
Diethyl Ether	1	595	99.9%	
Diethylamine	<1	587	99.5%	
Di-isobutyl Ketone	10	1141	80%	
Dimethyl Sulfoxide	8	501	99.90%	
Dibutyl Phthalate	>480	Not Detected	99%	
1,4-Dioxane	<1	707	99.4%	
Ethanol	7	296	99.5+%	
Ethanolamine	>480	Not Detected	99%	
Ethidium Bromide	90	0.68		
Ethylene Glycol	>480	Not Detected	99.8%	
Formaldehyde	110	0.172	37%	
Formic Acid	6	0.554	88%	
2-Furaldehyde	<1	385	99%	
Glutaraldehyde	>480	Not Detected	50%	
Heptane	145	0.73	99+%	
n-Hexane	16	55.3	99+%	
Hydrazine	31	40.2	98%	
Hydrochloric Acid	16	29.2	37%	
Hydrochloric Acid	>480	Not Detected	10%	

Chemical Resistance Guide

Chemical Name	Permeation Time (minutes) <i>ASTM F739-99A</i>	Permeation Rate (pg/cm ² /min) <i>ASTM F739-99A</i>	Concentration	Color Code Rating
Hydrogen Peroxide	>480	Not Detected	30%	Green
Isopropyl Alcohol (IPA)	29	38.6	99.50%	Yellow
Jet Fuel (Kerosene)	82	0.259	Mixture	Green
Lactic Acid	>480	Not Detected	85%	Green
Methanol	<1	257	99.8%	Red
1-Methoxy 2-Propanol	>480	Not Detected	99.5%	Green
1-Methyl 2-Pyrrolidinone	3	398	99%	Red
Methyl Methacrylate	<1	803	99%	Red
Mineral Spirits	105	1.6	mixture	Green
Morpholine	1	349	99%	Red
Naphtha	122	0.139	99%	Green
Nitric Acid	1	197	70%	Red
Nitric Acid	277	197	10%	Green
Nitromethane	<1	490	99%	Red
Nitropropane	<1	715	98%	Red
Octane	>480	Not Detected	99%	Green
Octanol	235	0.85	99+ %	Green
Oleic Acid	>480	Not Detected	99%	Green
Pentane	208	0.118	99%	Green
Phenol	6	120	99%	Red
Phosphoric Acid	>480	Not Detected	85%	Green
Potassium Hydroxide	>480	Not Detected	50%	Green
Propyl Acetate	<1	819	99.5%	Red
Propylene Glycol	>480	Not Detected	99%	Green
Pyridine	<1	635	99%	Red
Sodium Hydroxide	>480	Not Detected	50%	Green
Sodium Hypochlorite (Bleach)	>480	Not Detected	10-13%	Green
Stoddard Solvent	207	0.78	mixture	Green
Styrene	<1	836	99%	Red
Sulfuric Acid	>480	Not Detected	47.0%	Green
Sulfuric Acid	1	197	95-98%	Red
Tetrachloroethylene	3	11	99.9%	Red
Trichloroethylene	<1	1054	99%	Red
Triethanolamine	>480	Not Detected	98%	Green
Turpentine	115	0.361	Mixture	Green
o-Xylene	1	852	98%	Red

Kimberly-Clark warrants that its products comply with K-C's standard specifications as of the delivery date to K-C's authorized distributors/direct purchasers. Except to the extent prohibited by applicable law: 1) **THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE;** 2) K-C is not liable for any kind of special, incidental, or consequential damages; and 3) K-C's liability for breach of contract, tort, or other cause of action shall not exceed the product purchase price. Purchasers and users are deemed to have accepted the above warranty and limitation of liability, and cannot change the terms by verbal agreement or by any writing not signed by K-C. To the extent required by applicable law, K-C does not limit its liability for death/injury resulting from K-C's negligence.

®/™Trademarks of Kimberly-Clark Worldwide, Inc. or its affiliates. Marques déposées de Kimberly-Clark Worldwide, Inc. ou de ses filiales.

The COLOR GREY is a Trademark of KCWW. The COLOR PURPLE is a Registered Trademark of KCWW. ©2009 KCWW. Printed in the USA. K01504 K2365-09-01 06/09

Effective June 2009